

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
31 October 2002 (31.10.2002)

PCT

(10) International Publication Number
WO 02/086025 A1

(51) International Patent Classification⁷: C10G 65/08

(21) International Application Number: PCT/EP02/04417

(22) International Filing Date: 19 April 2002 (19.04.2002)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
01400996.3 19 April 2001 (19.04.2001) EP

(71) Applicant (*for all designated States except US*): SHELL
INTERNATIONALE RESEARCH MAATSCHAPPIJ
B.V. [NL/NL]; Carel van Bylandtlaan 30, NL-2596 HR
The Hague (NL).

(72) Inventors; and

(75) Inventors/Applicants (*for US only*): COLLIN, Marc


[FR/FR]; Route Departementale no. 3, F-76650 Petit
Couronne (FR). DUPREY, Eric [FR/FR]; Route Departementale
no. 3, F-76650 Petit Couronne (FR).

(81) Designated States (*national*): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG,
SI, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ,
VN, YU, ZA, ZM, ZW.

(84) Designated States (*regional*): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW),
Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR,
GB, GR, IE, IT, LU, MC, NL, PT, SE, TR), OAPI patent

[Continued on next page]

(54) Title: PROCESS TO PREPARE A BASE OIL HAVING A HIGH SATURATES CONTENT



(57) Abstract: Process to prepare a base oil having a saturates content of more than 90 wt%, a sulphur content of less than 0.03 wt% and a viscosity index of between 80 and 120 from a solvent refined base oil feedstock, which process comprises: (a) contacting the solvent refined base oil feedstock in the presence of a hydrogen containing gas in a first reaction zone containing one or more fixed beds of a catalyst, which catalyst comprises at least one Group VIB metal component and at least one non-noble Group VIII metal component supported on a refractory oxide carrier; (b) contacting the effluent of step (a) in the presence of a hydrogen containing gas in a second reaction zone containing one or more fixed beds of a catalyst, which catalyst comprises a catalyst comprising a noble metal component supported on an amorphous refractory oxide carrier, wherein the oil feedstock in step (a) flows counter-current to the upflowing hydrogen containing gas.

WO 02/086025 A1

WO 02/086025 A1



(BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, MI, MR,
NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

— with international search report

PROCESS TO PREPARE A BASE OIL HAVING A HIGH SATURATES
CONTENT

The invention is directed to a process to prepare a base oil having a saturates content of more than 90 wt%, a sulphur content of less than 0.03 wt% and a viscosity index of between 80 and 120 from a solvent refined base oil feedstock. Such a base oil is sometimes referred to as an API Group II base oils as defined in API Publication 1509: Engine Oil Licensing and Certification System, "Appendix E-API Base Oil Interchangeability Guidelines for Passenger Car Motor Oil and Diesel Engine Oils". There exists an increasing demand for these products due to the fact that modern automobile engines operate under more severe conditions, requiring a lubricating oil which is formulated based on a base oil having the above specifications. The API Group II base oils are also valuable for Industrial Lubricants, because of their improved inhibited oxidation stability.

A process to prepare API Group II base oils is described in WO-A-0073402 This patent publication describes the preparation of such a base oil from a petroleum fraction boiling in the lubricating oil range by first removing part of the aromatic compounds from a by means of solvent extraction, subsequently dewaxing the solvent extracted product and hydrotreating the dewaxed oil using a suitable sulphided hydrotreating catalyst. The effluent of the hydrotreating step is subsequently separated into a gaseous fraction and a liquid fraction; wherein the liquid fraction has a sulphur content of between 50 and 1000 ppmw and a nitrogen content of less than 50 ppmw. This liquid fraction is subjected to a second hydrotreating step using a catalyst comprising a

noble metal component supported on an amorphous refractory oxide carrier.

The above process is not preferred because it involves many process steps to obtain the desired base oil.

US-A-3673078 discloses a counter-current contacting of a solvent refined base oil using a platinum on alumina catalyst. The temperature in the bottom catalyst bed was 343 °C and the difference between the temperature in the top and the bottom catalyst bed was about 14 °C.

Although the disclosed processes may be used to prepare low sulphur and low polar compounds containing base oils there is still room for improvement.

The present invention therefore aims at providing a simple process, which can also reduce the sulphur and polar compounds level in an improved manner.

This is achieved by the following process. Process to prepare a base oil having a saturates content of more than 90 wt%, a sulphur content of less than 0.03 wt% and a viscosity index of between 80 and 120 from a solvent refined base oil feedstock, which process comprises:

- (a) contacting the solvent refined base oil feedstock in the presence of a hydrogen containing gas in a first reaction zone containing one or more fixed beds of a catalyst, which catalyst comprises at least one Group VIB metal component and at least one non-noble Group VIII metal component supported on a refractory oxide carrier;
- (b) contacting the effluent of step (a) in the presence of a hydrogen containing gas in a second reaction zone containing one or more fixed beds of a catalyst, which catalyst comprises a catalyst comprising a noble metal component supported on an amorphous refractory oxide carrier, wherein the oil feedstock

in step (a) flows counter-current to the upflowing hydrogen containing gas.

It has been found that with the process according to the invention a more simple process is obtained, wherein
5 a separate gas/liquid separation of the prior art process is not needed. In contrast the present process makes it possible to perform both hydrotreating steps in one vessel. This makes the process even more simple. A further advantage is that the present process can be used
10 in combination with existing solvent refined base oil processes. Such processes can be modified by adding the hydroprocessing steps (a) and (b) to the existing line-up. Most preferably existing hydrofinishing reactors which are usually part of an existing solvent refining
15 base oil process can be retrofitted to a reactor vessel comprising the first and second reaction zones of the process according to the invention. Alternatively solvent refined base oils prepared at a different location can be upgraded to API Group II base oils with the process
20 according to the present invention. Furthermore an API Group II base oil product having an excellent colour can be obtained in a high yield based on the solvent refined base oil feedstock using a process which operates at a relatively low pressure.

25 The solvent refined base oil feedstock will typically have a saturates content of below 90 wt% and is obtained by solvent extraction and solvent dewaxing of a petroleum fraction boiling in the lubricating oil range. Suitable distillate petroleum fractions are vacuum distillate
30 fractions derived from an atmospheric residue, i.e. distillate fractions obtained by vacuum distillation of a residual fraction which in return is obtained by atmospheric distillation of a crude oil. The boiling range of such a vacuum distillate fraction is usually
35 between 300 and 620 °C, suitably between 350 and 580 °C.

However, deasphalted residual oil fractions, including both deasphalted atmospheric residues and deasphalted vacuum residues, may also be applied.

5 Solvent extraction is a widely applied technology when preparing base oils and is for example described in "Lubricating base oil and wax processing", by Avilino Sequeira, Jr., 1994, Marcel Dekker Inc. New York, pages 81-118. Solvent extraction is suitably performed with for example N-methyl-2-pyrrolidone, furfural, phenol and sulphur dioxide as extraction solvent. Often used
10 solvents are N-methyl-2-pyrrolidone and furfural. In the solvent extraction aromatic compounds are partly removed from the hydrocarbon mixture, thereby increasing the viscosity index of the product. Amounts of sulphur and
15 nitrogen are also removed in the solvent extraction process.

Solvent dewaxing is also a widely applied technology when preparing base oils. Possible solvent dewaxing methods are described in the earlier mentioned textbook
20 "Lubricating base oil and wax processing", by Avilino Sequeira, Jr., 1994, Marcel Dekker Inc. New York, pages 153-224. Solvent dewaxing is performed by chilling the feedstock with a solvent whereby the wax molecules crystallise. The wax crystals are subsequently removed by
25 filtration and the solvent is recovered. Examples of possible solvents are methylethylketone/toluene, methylisobutylketone, methylisobutylketone/methylethylketone, dichloroethylene/methylenechloride, and propane.

The solvent refined base oil feedstock which is fed
30 to step (a) will typically contain less than 90 wt% saturates and have a sulphur content of between 300 ppmw and 2 wt%. The process according to the invention has been found to perform particularly good compared to prior art processes when the feedstock contains relatively high
35 amounts of sulphur, like more than 1000 ppmw. The

nitrogen content is preferably less than 50 ppmw. The saturates content is preferably higher than 70 wt%. Next to saturates the base oil mainly consists of aromatic and polar compounds. Examples of polar compounds are specific sulphur and nitrogen containing compounds. The pour point is usually less than 0 °C. Particularly suitable solvent refined base oil feedstocks to be used in the present invention are those which are classified as API Group I Base Oils as described in the afore-mentioned API Publication 1509: Engine Oil Licensing and Certification System, "Appendix E-API Base Oil Interchangeability Guidelines for Passenger Car Motor Oil and Diesel Engine Oils".

In the first hydrotreating step (a) the level of sulphur and nitrogen in the liquid flowing downwards through the catalyst bed is reduced. Hydrogen sulphide and ammonia are formed in this step from the organic S- and N-containing compounds. By performing this step counter-current to the upflowing hydrogen gas ammonia and hydrogen sulphide are removed from the downflowing liquid oil and discharged from the first reaction zone with the upflowing gas stream. It has been found that this separation is sufficient to reduce the sulphur and nitrogen levels in the oil leaving the first reaction zone (a) to values which are acceptable for performing step (b).

Suitably hydrogen sulphide and ammonia are removed from the gaseous stream leaving step (a) resulting in a cleaned hydrogen containing gas, which is preferably recycled to step (b). Examples of suitable methods for removing hydrogen sulphide and ammonia are methods known in the art, such as an absorption treatment with a suitable absorption solvent, such as solvents based on one or more alkanolamines, for example mono-ethanolamine,

di-ethanol-amine, methyl-di-ethanolamine and di-iso-propanolamine.

5 The catalyst to be used in step (a) may be any
suitable hydrodenitrification (HDN) and hydro-
desulphurization (HDS) catalyst known to one skilled in
the art as for example described in Worldwide Catalyst
Report, Oil & Gas Journal Special, September 27, 1999,
pages 53-58. Other examples are described in
10 US-A-5855767. Suitable catalysts comprise at least one
Group VIB metal component and at least one non-noble
Group VIII metal component selected from the group of
iron, nickel or cobalt supported on a refractory oxide
carrier. Examples of suitable Group IVB metals are
molybdenum (Mo) and tungsten (W). Examples of suitable
15 non-noble Group VIII metals are nickel (Ni) and
cobalt (Co). Suitable catalysts include those catalysts
comprising as the non-noble Group VIII metal component
one or more of nickel (Ni) and cobalt (Co) in an amount
of from 1 to 25 percent by weight (wt%), preferably 2 to
20 15 wt%, calculated as element relative to total weight of
catalyst and as the Group VIB metal component one or more
of in an amount of from 5 to 30 wt%, preferably 10 to
25 25 wt%, calculated as element relative to total weight of
catalyst. These metal components may be present in
elemental, oxidic and/or sulphidic form and are supported
on a refractory oxide carrier. The catalyst may also
comprise a noble metal from Group VIII next to the above
mentioned metals. Examples of suitable noble metals are
palladium and platinum.

30 The refractory oxide support of the catalyst used in
the first hydrotreating step may be any inorganic oxide,
alumino-silicate or combination of these, optionally in
combination with an inert binder material. Examples of
suitable refractory oxides include inorganic oxides, such

as alumina, silica, titania, zirconia, boria, silica-alumina and mixtures of two or more of these.

Phosphorus (P), which is a well known promoter, may also be present in the catalyst used in the first
5 hydrotreating step. The phosphorous content is preferably between 1 and 10 wt% as oxide.

Preferred catalyst, more preferably containing a phosphorus promoter, are cobalt/molybdenum on alumina having a cobalt content of between 1-5 wt% as oxide and
10 10-25 wt% molybdenum content as oxide; nickel/molybdenum on alumina having a nickel content 1-5 wt% as oxide and a molybdenum content of between 10-30 wt% as oxide of which commercially available catalyst DN-190 of Criterion Catalyst Company (Houston, TX) is an example; and
15 nickel/tungsten on alumina having a nickel content of between 1-5 wt% as oxide and a tungsten content of between 10-30 wt% as oxide.

Since the base oil feed to be converted in step (a) will contain sulphur-containing compounds, the catalyst
20 used in the first hydrotreating step is at least partly sulphided prior to operation in order to increase its sulphur tolerance. Presulphiding of the catalyst can be achieved by in-situ or ex-situ methods known in the art, such as for instance those methods disclosed in the
25 following publications EP-A-181254, EP-A-329499, EP-A-448435, EP-A-564317, WO-A-9302793 and WO-A-9425157.

In general, presulphiding is effected by contacting the unsulphided catalyst with a suitable sulphiding agent, such as hydrogen sulphide, elemental sulphur, a
30 suitable polysulphide, a hydrocarbon oil containing a substantial amount of sulphur-containing compounds or a mixture of two or more of these sulphiding agents. Particularly for the in situ sulphidation a hydrocarbon oil containing a substantial amount of sulphur-containing
35 compounds may suitably be used as the sulphiding agent.

Such oil is then contacted with the catalyst at a temperature which is gradually increased from ambient temperature to a temperature of between 150 and 250 °C. The catalyst is to be maintained at this temperature for
5 between 10 and 20 hours. Subsequently, the temperature is to be raised gradually to the operating temperature. A particular useful hydrocarbon oil presulphiding agent may be the base oil feed itself, which contains a significant amount of sulphur-containing compounds. In this case the
10 unsulphided catalyst may be contacted with the feed under, for example, the operating conditions, thus causing the catalyst to become sulphided. Typically, the base oil feed should comprise at least 0.5% by weight of sulphur-containing compounds, said weight percentage
15 indicating the amount of elemental sulphur relative to the total amount of feedstock, in order to be useful as a sulphiding agent.

Step (a) is suitably operated as follows. The temperature is between 250 and 400 °C and preferably
20 between 300 and 370 °C. The actual temperature and other operating conditions will depend largely on the content of sulphur and/or nitrogen in the feed and the desired reduction to be achieved as described above. Higher temperatures, for example, result in higher reduction of
25 S- and N-content. The total pressure may range from 10 to 250 bar, but preferably is between 40 and 100 bar. The weight hourly space velocity (WHSV) may range from 0.1 to 10 kg of oil per litre of catalyst per hour (kg/l.h) and suitably is in the range from 0.2 to 5 kg/l.h.

30 In step (b) the liquid fraction obtained in step (a) is contacted in the presence of hydrogen and a catalyst comprising a Group VIII noble metal component supported on an amorphous refractory oxide carrier. In step (b) part of the aromatic compounds are hydrogenated to
35 saturated compounds. The catalyst preferably comprises at

least one noble Group VIII metal component supported on an amorphous refractory oxide carrier. Suitable noble Group VIII metal components are platinum and palladium. The catalyst suitably comprises platinum, palladium or both. The total amount of noble Group VIII metal component(s) present suitably ranges from 0.1 to 10 wt%, preferably 0.2 to 5 wt%, which weight percentage indicates the amount of metal (calculated as element) relative to total weight of catalyst.

It has been found particularly important that the catalyst comprises an amorphous refractory oxide as the carrier material. Examples of suitable amorphous refractory oxides include inorganic oxides, such as alumina, silica, titania, zirconia, boria, silica-alumina, fluorided alumina, fluorided silica-alumina and mixtures of two or more of these. Of these, amorphous silica-alumina is preferred, whereby silica-alumina comprising from 5 to 75 wt% of alumina has been found to be particularly preferred. Examples of suitable silica-alumina carriers are disclosed in WO-A-9410263. Examples of suitable catalysts are catalyst comprising platinum or palladium on an amorphous silica-alumina carrier. More preferably the catalyst comprises platinum and palladium supported on an amorphous silica-alumina carrier. A most preferred catalyst comprises an alloy of palladium and platinum preferably supported on an amorphous silica-alumina carrier of which the commercially available catalyst C-624, C-634, C-652 and C-654 of Criterion Catalyst Company (Houston, TX) are examples. These platinum/palladium catalyst are advantageous because they deactivate less when the sulphur content of the liquid effluent of step (a) is relatively high as can be the case in the present invention. The hydrogen containing gas flows counter-current to the oil feedstock in step (a). In step (b) the hydrogen containing gas may flow co-

current or counter-current. The co-current option may be chosen when steps (a) and (b) are performed in different vessels, while the counter-current option may be chosen when steps (a) and (b) are performed in one vessel.

5 Suitably the temperature in step (b) is equal or lower than the temperature in step (a). More preferably the temperature in step (b) is more than 30 °C, even more preferably more than 35 °C and most preferably more than 40 °C lower than in step (a). In a situation wherein the
10 hydrogen containing gas flows counter-current in both steps (a) and (b) the temperature in steps (a) and (b) can be controlled by adjusting the temperature of the solvent refined feedstock and/or the hydrogen fed to step (b). Optionally additional hydrogen having a higher
15 temperature can be fed directly to step (a) in order to achieve a higher reaction temperature in this step. Optionally the temperature in steps (a) and (b) can be controlled by indirect heat exchange in the catalyst beds themselves, for example by means of heat exchange tubes
20 present in these beds. The temperature of the feed to step (b) can also be reduced by cooling the effluent of step (a) in an external heat exchanger before feeding it to step (b). With external heat exchanger is meant any indirect heat exchanger placed outside the vessel
25 containing the catalyst beds. This option can be used when steps (a) and (b) are performed in one vessel or in separate vessels. In case steps (a) and (b) are performed in one vessel the effluent of step (a) can be withdrawn by means of a so-called withdraw tray. Suitably cooling
30 of the effluent of step (a) before being used in step (b) can be achieved by recycling part of the, suitably cooled, effluent of step (b) to step (b).

35 The total pressure in steps (a) and (b) are suitably the same when the fixed catalyst beds of the first reaction zone (a) are placed in the same vessel as the

catalyst beds of the second reaction zone (b). This will be referred to as the stacked-bed embodiment. The temperature in step (b) will suitably not exceed 350 °C and preferably is in the range of from 150 and 350 °C, more preferably from 250 to 320 °C. The operating total pressure may range from 10 to 250 bar and preferably is in the range of from 40 to 100 bar. The WHSV may range from 0.1 to 10 kg of oil per litre of catalyst per hour (kg/l.h) and suitably is in the range from 0.5 to 6 kg/l.h.

In the stacked-bed embodiment the fixed catalyst bed(s) of the first reaction zone (a) are placed above the catalyst bed(s) of the second reaction zone (b).

Optionally an additional catalytic dewaxing or isodewaxing step can be performed on the solvent refined base oil feedstock. This may be advantageous when low pour points are desired. Preferably such a pour point reducing step is performed after step (a) and before step (b). It may be performed in a counter-current mode as in step (a). Optionally when this pour point reducing treatment is performed in a separate vessel than step (a) co-current contacting of the effluent of step (a) and hydrogen in the presence of a suitable catalyst is also possible. The catalytic dewaxing can be performed by any process wherein in the presence of a catalyst and hydrogen the pour point of the base oil precursor fraction is reduced as specified above. Suitable dewaxing catalysts are heterogeneous catalysts comprising a molecular sieve and optionally in combination with a metal having a hydrogenation function, such as the Group VIII metals. Molecular sieves, and more suitably intermediate pore size zeolites, have shown a good catalytic ability to reduce the pour point of a base oil precursor fraction under catalytic dewaxing conditions. Preferably the intermediate pore size zeolites have a

pore diameter of between 0.35 and 0.8 nm. Suitable intermediate pore size zeolites are ZSM-5, ZSM-12, ZSM-22, ZSM-23, SSZ-32, ZSM-35 and ZSM-48. Another preferred group of molecular sieves are the silica-aluminaphosphate (SAPO) materials of which SAPO-11 is most preferred as for example described in US-A-4859311. ZSM-5 may optionally be used in its HZSM-5 form in the absence of any Group VIII metal. The other molecular sieves are preferably used in combination with an added Group VIII metal. Suitable Group VIII metals are nickel, cobalt, platinum and palladium. Examples of possible combinations are Ni/ZSM-5, Pt/ZSM-23, Pd/ZSM-23, Pt/ZSM-48 and Pt/SAPO-11. Further details and examples of suitable molecular sieves and dewaxing conditions are for example described in WO-A-9718278, US-A-5053373, US-A-5252527 and US-A-4574043.

A preferred class of dewaxing catalysts comprise intermediate zeolite crystallites as described above and a low acidity refractory oxide binder material which is essentially free of alumina as described above, wherein the surface of the aluminosilicate zeolite crystallites has been modified by subjecting the aluminosilicate zeolite crystallites to a surface dealumination treatment. A preferred dealumination treatment is by contacting an extrudate of the binder and the zeolite with an aqueous solution of a fluorosilicate salt as described in for example US-A-5157191 or WO-A-0029511. Examples of suitable dewaxing catalysts as described above are silica bound and dealuminated Pt/ZSM-5, silica bound and dealuminated Pt/ZSM-23, silica bound and dealuminated Pt/ZSM-12, silica bound and dealuminated Pt/ZSM-22, as for example described in WO-A-0029511 and EP-B-832171.

Possible preferred embodiments of the present invention are illustrated in Figures 1-2. Figure 1 shows

one vessel (1) provided with an inlet (2) for receiving solvent refined base oil feedstock, an inlet (3) for fresh hydrogen, an outlet (4) for used hydrogen and an outlet (5) for the desired base oil product. The vessel (1) is furthermore provided with two catalyst beds (6) for performing step (a) and two catalyst beds (7) to perform step (b). The product effluent being discharged via line (8) is cooled in heat exchanger (9). Part of this cooled product may be recycled via (10) to a position (11) between the catalyst beds of step (a) and (b) to cool down the effluent of step (a) before it contacts the catalyst beds of step (b). The hydrogen being discharged via outlet (4) will be freed from hydrogen sulphide and ammonia in a cleaning unit (not shown) before being recycled to step (b).

Figure 2 shows a two vessel configuration consisting of a first vessel (12) provided with a inlet (13) for receiving solvent refined base oil feedstock, an inlet (14) for receiving hydrogen, an outlet (15) for non-consumed hydrogen and an outlet (16). The vessel (12) is provided with two catalyst beds (17) for performing step (a) in a counter-current operation. Figure 2 also shows a second vessel (18) for performing step (b) in a co-current mode of operation. As a top catalyst bed (19) in vessel (18) a dewaxing or isodewaxing catalyst may optionally be present. Vessel (18) is further provided with a one or more catalyst beds (20) for performing step (b). The effluent of vessel (12) may be reduced in temperature in heat exchanger (21). The feed to vessel (18) is mixed with fresh hydrogen (22). The vessel (18) is further provided with a outlet (23) for the desired base oil product. From this product non-consumed hydrogen is separated in gas-liquid separator (24). This hydrogen may suitably be directly used as feed to vessel (12) via inlet (14). The hydrogen

being discharged via outlet (15) will be freed from hydrogen sulphide and ammonia in a cleaning unit (not shown) before it is re-used via hydrogen supply means (22).

5 The invention will be illustrated by the following non-limiting examples.

Example 1

10 A solvent refined base oil obtained by performing an extraction with furfural on a vacuum distillate followed by a solvent dewaxing step using methylethylketone/toluene having the properties as listed in Table 1 was continuously fed to the top of a stacked bed reactor. The top catalyst bed consisted of a commercial NiMo on alumina catalyst (DN-190 of Criterion Catalyst Company (Houston, TX)). The bottom bed contained bed consisted of a commercial PtPd on amorphous silica-alumina carrier (C-624 of Criterion Catalyst Company (Houston, TX)). To the bottom of the stacked bed reactor hydrogen was continuously fed. The operating conditions were a hydrogen partial pressure of 80 bar, a WHSV of 1 kg/l/h in the top catalyst bed and a WHSV of 0.87 kg/l/h in the bottom catalyst. The fresh hydrogen inlet flow was 65 Nl/h. The temperature in the top bed was 350 °C and the temperature in the second bed was 320 °C.

25 The properties of the base oil product leaving the stacked-bed reactor is presented in Table 1.

Example 2

30 Example 1 was repeated, except in that the temperature in the bottom bed was 290 °C. The properties of the final base oil product are in Table 1.

Example 3

 Example 1 was repeated, except in that the temperature in the bottom bed was 310 °C and the temperature in the top bed was 340 °C. The properties of the final base oil product are in Table 1.

TABLE 1

	base oil feed- stock	API Group II BASE OIL	API Group II BASE OIL	API Group II BASE OIL
Example	feed	1	2	3
temperature 1 st reaction zone (°C)	-	350	350	340
temperature 2 nd reaction zone (°C)	-	320	290	310
saturates (wt%)	72.8	98.2	98.7	98.1
polars (wt%)	27.2	1.8	1.3	1.9
sulphur (mg/kg)	7700	2	5	8
nitrogen (mg/kg)	23	<1	<1	<1
Viscosity Index	104	109	107	107
viscosity at 100 °C (cSt)	5.2	4.1	4.6	4.4
viscosity at 40 °C (cSt)	29.5	20.0	23.9	22.5
pour point (°C)	-16	-11	-11	-11
colour Saybolt		+26	+28	+27

C L A I M S

1. Process to prepare a base oil having a saturates content of more than 90 wt%, a sulphur content of less than 0.03 wt% and a viscosity index of between 80 and 120 from a solvent refined base oil feedstock, which process
5 comprises:

(a) contacting the solvent refined base oil feedstock in the presence of a hydrogen containing gas in a first reaction zone containing one or more fixed beds of a catalyst, which catalyst comprises at least one
10 Group VIB metal component and at least one non-noble Group VIII metal component supported on a refractory oxide carrier;

(b) contacting the effluent of step (a) in the presence of a hydrogen containing gas in a second reaction
15 zone containing one or more fixed beds of a catalyst, which catalyst comprises a catalyst comprising a noble metal component supported on an amorphous refractory oxide carrier, wherein the oil feedstock in step (a) flows counter-current to the upflowing
20 hydrogen containing gas.

2. Process according to claim 1, wherein the solvent refined base oil feedstock comprises between 300 ppm and 2 wt% sulphur, and between 70 and 90 wt% saturates.

3. Process according to any one of claims 1-2, wherein
25 the catalyst used in step (a) is a catalyst comprising cobalt, molybdenum and an alumina support, nickel/molybdenum and an alumina support or nickel, tungsten and an alumina support.

4. Process according to any one of claims 1-3, wherein
30 the catalyst used in step (b) comprises an alloy of platinum and palladium and a silica-alumina support.

5. Process according to any one of claims 1-4, wherein the temperature in step (a) is between 300 and 370 °C and the temperature in step (b) is between 250 and 320 °C.
6. Process according to claim 5, wherein the temperature in step (b) is more than 35 °C lower than in step (a).
7. Process according to any one of claims 1-6, wherein the total pressure in steps (a) and (b) are between 40 and 100 bar.
8. Process according to any one of claims 1-7, wherein step (b) is performed such that the effluent of step (a) flows counter-current to the upflowing hydrogen containing gas.
9. Process according to claim 8, wherein steps (a) and (b) are performed in one vessel.
10. Process according to claim 9, wherein the effluent of step (a) is reduced in temperature by mixing it with part of the effluent of step (b), which has been reduced in temperature relative to the temperature of step (b).
11. Process according to any one of claims 1-10, wherein prior to step (b) a catalytic (iso)dewaxing step is performed on the effluent of step (a).
12. Process according to claim 11, the (iso)dewaxing step and step (b) are performed co-current with a hydrogen containing gas in a separate vessel from the vessel in which step (a) is performed.

Fig.1.





Fig.2.



INTERNATIONAL SEARCH REPORT

International Application No

PCT/EP 02/04417

A. CLASSIFICATION OF SUBJECT MATTER
IPC 7 C10G65/08

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C10G

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 3 673 078 A (KIRK MERRITT C JR) 27 June 1972 (1972-06-27) column 1, line 60 -column 3, line 5 column 3, line 35-57; figure 3 column 5, line 62-75; example III ---	1-9
X	GB 1 381 004 A (EXXON RESEARCH ENGINEERING CO) 22 January 1975 (1975-01-22) page 1, line 53-80 page 3, line 75-130; examples 1-3; tables I-VII page 4, line 91-111 ---	1-8
Y	US 5 976 354 A (POWERS JOHN ROBERT ET AL) 2 November 1999 (1999-11-02) column 3, line 1 -column 7, line 39; figure 1 column 11, line 37-40; claim 1 ---	1-9
-/--		

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

1 August 2002

Date of mailing of the international search report

07/08/2002

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Kazemi, P

INTERNATIONAL SEARCH REPORT

International Application No

PCT/JP02/04417

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	DE 29 35 191 A (METALLGESELLSCHAFT AG) 2 April 1981 (1981-04-02) page 7, last paragraph; claim 2 page 9, line 25-30; figure 1 ---	1-9
Y	US 5 935 416 A (LETA DANIEL P ET AL) 10 August 1999 (1999-08-10) column 2, line 23 -column 3, line 63 column 4, line 16-22 column 5, line 15-20 column 5, line 60 -column 6, line 20 column 6, line 65 -column 7, line 7 column 8, line 13-28; claims 1-3,7,9; example 7 ---	1-7
Y	WO 98 02502 A (CHEVRON USA INC) 22 January 1998 (1998-01-22) page 3, line 14-32; claims 1,5,17; examples 3-5,7,8; tables III,VI page 8, line 4-26 page 12, line 14-24 -----	1-7

INTERNATIONAL SEARCH REPORT
Information on patent family members

International Application No

PCT/EP 02/04417

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
US 3673078	A	27-06-1972	CA 952459 A1 US 3788976 A	06-08-1974 29-01-1974
GB 1381004	A	22-01-1975	NONE	
US 5976354	A	02-11-1999	NONE	
DE 2935191	A	02-04-1981	DE 2935191 A1 ZA 8004921 A	02-04-1981 26-08-1981
US 5935416	A	10-08-1999	US 5976353 A AU 743100 B2 AU 2676699 A CA 2319145 A1 EP 1054940 A1 JP 2002503757 T WO 9941338 A1 AU 718741 B2 AU 3641997 A CA 2257918 A1 EP 0907697 A1 JP 2002509562 T WO 9800479 A1 US 6325918 B1 US 5911874 A US 2002038777 A1	02-11-1999 17-01-2002 30-08-1999 19-08-1999 29-11-2000 05-02-2002 19-08-1999 20-04-2000 21-01-1998 08-01-1998 14-04-1999 26-03-2002 08-01-1998 04-12-2001 15-06-1999 04-04-2002
WO 9802502	A	22-01-1998	AU 724570 B2 AU 3716597 A BR 9710321 A CA 2260104 A1 CN 1225662 A CZ 9900097 A3 EP 0912659 A1 HU 0003145 A2 JP 2001525861 T PL 331039 A1 TR 9900098 T2 WO 9802502 A1 US 6264826 B1 US 5993644 A	28-09-2000 09-02-1998 17-08-1999 22-01-1998 11-08-1999 14-04-1999 06-05-1999 28-02-2001 11-12-2001 21-06-1999 21-04-1999 22-01-1998 24-07-2001 30-11-1999

THIS PAGE BLANK (USPTO)